

Product Information Sheet

IGP-DURA[®]sky 95

Hyper durable, high-performance powder coatings for long-lasting aesthetic surfaces.

Extremely weather-resistant, fluoropolymer-based premium powder coating engineered to deliver long-lasting protection for high-end architectural surfaces. Designed for maximum durability, it withstands extreme climatic conditions such as intense UV irradiation, abrasive wear, and salty air in marine environments. The system meets the US standards of AAMA 2605-20 and complies with the European Quality Association's Qualicoat Class 3 requirements, ensuring superior performance and reliability in demanding applications.

Properties

- Ultra super durable facade quality, 10 years Florida
- Anti-Graffiti
- Clean Effect

Approvals

- QC Class 3 approved
- EPD according to EN 15804+A2
- AAMA 2605-20 Test Report



Key Features

- Lasting value retention through extremely weather-resistant fluoropolymer powder coating.
- Cost-efficient maintenance thanks to dirt-repellent properties and excellent cleanability.
- Elegant and durable matte surfaces due to a robust finish with higher resistance to abrasive and mechanical stress.
- Long-term security with a warranties of up to 25 years.
- Effective graffiti protection through exceptionally high resistance to aggressive solvent-based anti-graffiti cleaners.
- Environmentally beneficial thanks to good adhesion on chromium-free pretreatments.
- Certified quality standards and transparent warranty systems that build trust and provide long-term planning reliability.

Surface finishes / available range



95

IGP-DURA[®]sky 9503

Appearance

- Matte
- 25-35 R˘ 60°
- Smooth finish

Available Effects

- Uni, without effect
- Pearl mica

Further details to the product groups and possible effect options are available on the IGP website under: <https://igp-powder.com/en/architecture-exterior/igp-dura-sky-95>

Further Information

Substrate and Pre-treatment

Possible substrates for application are aluminium, steel and galvanised steel. The substrate must be free of oil, grease and oxidation products. Pre-treatment depends on the type of substrate and the level of corrosion protection required. Further information are available in the technical data sheet.

For white and light IGP-DURA[®]sky qualities, the use of IGP-KORROPRIMER 6007A90164A01 is mandatory as a primer. For improved corrosion protection for applications on steel or galvanised steel, the use of corrosion protection primer IGP-KORROPRIMER 60 is recommended.

Paint removal and disposal

After use, coated goods should be supplied to the normal recycling process. The disposal methods for sludges or residual powders must be observed in accordance with the local official provisions whilst taking Waste Code "080201 Coating Powder Wastes" in accordance with the European Waste Catalogue into consideration.